

Single-Sided Release Paper with PE Laminated Back

SLK-70AW



Tokyo Sales Group +81-3-6837-9052

Osaka Sales Group +81-6-6228-1180

Structure

Silicone/PE(mirror)/Wood-free paper(white)70g/m²/PE(matt)

Characteristics

1. Light to medium release
2. Non-migration
3. Superior exposure resistance

Typical properties

Item (unit)	Measurement value		Testing method
Total thickness (μm)	110		JIS P-8118
Basis weight of release liner (g/m ²)	105		JIS P-8124
Tensile strength (kN/m)	MD	6.5	JIS P-8113
	CD	4.5	
Tear strength (mN)	MD	500	JIS P-8116
	CD	500	
Release force (N/m)	15		※1
Residual adhesion ratio (%)	98		※2

※1

Adhesive: Oribain BPS-8170

Laminating paper:

Wood-free paper 78g/m²

Peeling speed: 5m/min

Peeling angle: 180°(tape release)

※2

Standard tape: Nitto 31B

Standard board:

Stainless plate (#280)

Peeling speed: 0.3 m/min

Peeling angle: 180°

These values are representative values, not standard values. Peel load and residual adhesion rate vary greatly depending on the measurement conditions, so please check the quality under your own conditions before use.